

**NOVAFINA COVER** 

Levelling compound for walls for external and internal use

- **▷** Excellent workability
- **▶** Excellent covering
- **▷** Smooth finish
- **▶** Resistant to weathering
- ▶ Can be applied with airless spray systems

Description	NOVAFINA COVER is a cementitious spatula putty enriched with synthetic resins and special additives. It is suitable for external and internal applications, has excellent workability, covers imperfections and poor workmanship, and provides a smooth final surface with high resistance to moisture and frost.
Certifications	CE Marking with Declaration of Performance (DoP) C06570-CPR-2250304 as a general-purpose rendering mortar for applications in internal and external walls, columns and partitions according EN 998-1, GP CS II W1.

# **Typical Applications**

#### NOVAFINA COVER is suitable for:

- Cement based walls and ceilings before applying the paint
- For filling bad structured concretes and plasters
- · Cement boards and concrete walls
- Gypsum boards after priming with NOVADUR W or NOVAPRIMER
- No cracks, no shrinking even at high film thickness
- For an application thickness of 1 10 mm
- · Suitable for airless spray systems

www.novamix.gr 1 / 4



### **Technical Data**

#### **Product Identification**

Consistency - Color	Powder - white
Chemical base	Portland cement, aggregates, special additives
Granulometry	D <sub>max</sub> : 0.2 mm
Apparent weight	1,2 ± 0,1 kg/L

## **Application Data (+23°C % & 50% R.H.)**

Mixing ratio	8.0 – 9.0 L water per 25 kg
Specific gravity of the mix	$1.4 \pm 0.1 \text{ kg/L}$
Dry mortar density	$1.1 \pm 0.05 \text{ kg/L}$
Temperature application	from +5°C up to +35°C
Pot life	>4 hours

Final Performances according to EN 998-1:2016	Performance
Compressive strength	CS II
Adhesion	≥ 0,5 N/mm <sup>2</sup>
Capillary water absorption	W1
Water vapour permeability coefficient (µ)	µ ≤ 20
Thermal conductivity mean (λ <sub>10,dry,mat</sub> )	0,33 W/mk
Reaction to fire	A1

## **Application Procedure**

## **Substrate preparation**

Cement based substrates must be compact, without cracks, free of dust, salts, grease and any other materials that could reduce adhesion of NOVAFINA COVER to them. If the application is made on very absorbent substrates and / or at high temperatures, it recommended a good substrate wetting, avoiding the presence of standing water. Where substrates of reduced strength proceed priming with NOVAPRIMER. For more information, please refer to the corresponding Product Data Sheets.

www.novamix.gr 2 / 4



Preparation	Mix the NOVAFINA COVER bag (25 kg) with $8.0-9.0$ liters of clean water with a low-speed electric mixer for at least $3-5$ minutes. Mixing should take place until the mixture is completely uniform and free of lumps. The product is ready for use. The mixture has approximately 4-5 hours of pot life.
Application	The mix is applied with a spatula or airless spray systems in one or more layers at a total thickness not exceeding 10 mm. The waiting time between layers must be 3 - 4 hours depending on the temperature and the humidity of the environment.
Recommendations	<ul> <li>Do not apply when substrate and ambient temperatures are below +5°C and higher than +35°C</li> <li>Do not apply upon metal or wood or surfaces such as polyurethane, acrylic, paints and substrates subjected to big movements</li> <li>Do not apply upon PVC membranes, bituminous membranes and other materials that polymerize in the long ran</li> <li>Do not apply upon loose substrates or substrates with insufficient cure</li> <li>Do not apply upon non-absorbent substrates without proper preparation</li> <li>Do not cover existing expansion joints of the substrate</li> <li>Do not apply during direct sunlight and/or strong wind presence</li> <li>Do not exceed the recommended quantity of the mixing water</li> <li>Protect from rain or frost the first 24 hours</li> <li>Do not add cement, gypsum, lime or other additives that might affect the properties of the mortar</li> <li>Application to be performed by professional users</li> </ul>
Consumption	Approx. 1.2 kg/m²/mm
Cleaning	Buckets, tools, coatings etc. can be cleaned with water as long as the mix is still fresh. Once dried cleaning can be done only by mechanical means
Storage	NOVAFINA COVER remains stable for at least 12 months in the original sealed packaging stored in a dry place and temperature between +5°C and +35°C.
Packaging	Paper bags of 20 kg or plastic bag of 5 kg
Safety Instructions	For information and instructions regarding disposal and safe handling, users should refer to the latest Safety Data Sheet of the product containing ecological, toxicological and other safety-related data.

www.novamix.gr 3 / 4

Version: 06/2023. V.05



#### Legal notes

The technical data and recommendations contained or listed in this leaflet are the result of laboratory measurements, of our current knowledge and experience. All the above-mentioned information and specifications should in any case be considered as indicative, as they may differ from each other. The Company makes every effort to ensure the accuracy of the information provided herein. Product specifications, prices and availability are subject to change without notice and may differ from those shown.

In practice, variations in materials, substrates and on-site implementation conditions are such that no warranty can be given or implied, as to the merchantability or suitability of the materials for a particular purpose and for the exact conditions of each project. Anyone interested of using the product must be sure beforehand that the product is suitable for the intended use and in any case, the user is solely responsible for any consequences due to the use of the product. Among other things, the Company is not responsible for any normal wear or tear from environmental or other inappropriate conditions. We reserve the right to revise or change the data herein without prior notice.

Restrictions and disclaimers apply to the extent permitted by applicable law. The Company has a Technical Support Department, which is the only one responsible for providing technical advice and solutions to deal with problems. Requests to the Technical Support Department are addressed and answered, only in writing.

For the latest and a valid version of the Technical Data Sheet, the user of the material must refer to our website www.novamix.gr or directly to the QR Code of the product.













DOMOCHEMICAL S.A.
40 Papanikoli str.
Chalandri, 15232, Athens
T +30 210 68 93 953
F +30 210 68 94 571
novamix@novamix.gr

www.novamix.gr 4 / 4